

Cherry Andante

Product details / Technical properties

Article number	10041665 / KIGL3KTD	**Bevel**	square edged	**Moisture content**	5-9%
Wood	Cherry	**Number of slotted top layers**	0	**Fire protection classification**	Dfl-s1
Grading	Andante	**Surface structure**	unbrushed	**Content of formaldehyde**	E 1
Product type	3-layer parquet	**m² per carton**	2,84	**PCP content**	NPD
Format	14mm Longstrip 3-Strip	**Boards per carton**	6	**Brinell Value**	29
Dimensions	14 x 215 x 2200 mm	**Weight per carton (kg)**	21	**Shrinking and swelling**	
Top layer thickness	3,5 mm	**m² per pallet**	142	**Breaking strength**	NPD
Core material	Spruce / Spruce	**Boxes per pallet**	50	**Thermal conductivity (W/(m*K)**	0,12
Connection	5G Click	**Weight per pallet (kg)**	1050	**Thermal resistance (m²*K)/W**	0,12
Floor heating	suitable	**EN Norm**	EN 13489	**Antislip performance (CE)**	USRV 59
Treatment	Live Natural oil	**FSC claim**	controlled sources	**Antislip performance (DIN)**	R10
Appearance	Golden floors	**Performance classification**	Class 1	**Nobb.number**	
Colour		**Density**	>= 500kg/m³	**EAN Code**	7035580186588

CE
06
Boen AS
Topdalsveien 406-408, 4658 Tvedt, Norway
Parquet flooring according to EN 13489: 2017-12 and EN 14342:2013
9,5-23 mm total thickness,
parquet for indoor use
DOP 4658, NB 0766
Dfl-s1, El, density >= 500kg/m³
thermal conductivity >= 0,14 W/mK

Wood is a product of nature – each tree has its own structure and individual colour combination. An image or a sample will therefore never be able to give you a complete picture of the finished floor. Please also note that the colour may change when exposed to light. As a guideline, darker wood species will get a more golden tone, whereas lighter species will become slightly darker. Cracked knots are filled with putty, so small gaps between the putty and wood may appear.