

# Oak Espressivo

Product details / Technical properties

| | | | | | |
|---|---|---|---|---|---|
| **Article number** | 10109273 / GBG8ZKFD | **Bevel** | beveled 2V | **Moisture content** | 5-9% |
| **Wood** | Oak | **Number of slotted top layers** | 2 | **Fire protection classification** | Dfl-s1 |
| **Grading** | Espressivo | **Surface structure** | brushed | **Content of formaldehyde** | E 1 |
| **Product type** | 3-layer parquet | **m² per carton** | 3,04 | **PCP content** | NPD |
| **Format** | 14mm Plank 138 | **Boards per carton** | 10 | **Brinell Value** | 38 |
| **Dimensions** | 14 x 138 x 2200 mm | **Weight per carton (kg)** | 23,5 | **Shrinking and swelling** | |
| **Top layer thickness** | 3,5 mm | **m² per pallet** | 127,68 | **Breaking strength** | NPD |
| **Core material** | Spruce / Spruce | **Boxes per pallet** | 42 | **Thermal conductivity (W/(m*K)** | 0,129 |
| **Connection** | 5G Click | **Weight per pallet (kg)** | 987 | **Thermal resistance (m²*K)/W** | 0,109 |
| **Floor heating** | suitable | **EN Norm** | EN 13489 | **Antislip performance (CE)** | USRV 45 |
| **Treatment** | Live Natural oil | **FSC claim** | controlled sources | **Antislip performance (DIN)** | R10 |
| **Appearance** | Golden floors | **Performance classification** | Class 1 | **Nobb.number** | 52000703 |
| **Colour** | | **Density** | >= 500kg/m³ | **EAN Code** | 7035580197966 |

www.realwood.eu

www.blauer-engel.de/uz176

CE
06
Boen AS
Topdalsveien 406-408, 4658 Tvet, Norway
Parquet flooring according to EN 13489: 2017-12 and EN 14342:2013
9,5-23 mm total thickness,
parquet for indoor use
DOP 4658, NB 0766
Dfl-s1, El, density >= 500kg/m³
thermal conductivity >= 0,14 W/mK

Wood is a product of nature – each tree has its own structure and individual colour combination. An image or a sample will therefore never be able to give you a complete picture of the finished floor. Please also note that the colour may change when exposed to light. As a guideline, darker wood species will get a more golden tone, whereas lighter species will become slightly darker. Cracked knots are filled with putty, so small gaps between the putty and wood may appear.