



Oak White Animoso

Product details / Technical properties

Article number	10036344 (EIGV42FD)	Bevel	beveled 2V	Moisture content	5-9%
Wood	Oak	Number of slotted top layers	1	Fire protection classification	Cfl-s1
Grading	Animoso	Surface structure	sanded	Content of formaldehyde	E 1
Product type	3-layer parquet	m² per carton	2,76	PCP content	NPD
Format	14mm Plank Castle	Boards per carton	6	Brinell Value (N/mm²)	38
Dimensions	14 x 209 x 2200 mm	Weight per carton (kg)	24	Shrinking and swelling	
Top layer thickness	3.5 mm	m² per pallet	138	Breaking strength	NPD
Core material	Spruce / Spruce	Boxes per pallet	50	Thermal conductivity (W/(m²K))	0,129
Connection	5G Click	Weight per pallet (kg)	1200	Thermal resistance (m²K)/W	0,109
Floor heating	suitable	EN Norm	EN 13489	Antislip performance (CE)	USRV 33
Treatment	Live Matt lacquer	FSC claim	controlled sources	Antislip performance (DIN)	R9
Appearance	Light floors	Performance classification	Class 1	Nobb.number	46376706
Colour	White	Density	>= 500kg/m ³	EAN Code	7035580075820



TESTED PRODUCT
ID 0921 - 33879 - 003



CERTIFIED BY
SCS Global Services



REAL WOOD
www.realwood.eu



www.blauer-engel.de/uz176



CE

D6

Boen AS

Topdatumen: 404-404-4458 T-Net, Norway
Parquet flooring according to
EN 13489-2017-12 and EN 1492-2013
9,5-25 mm total thickness
parquet for indoor use

DOP 4658, NB 0766

Df-t; El. density >= 500kg/m³
thermal conductivity >= 0,14 W/mK

Wood is a product of nature – each tree has its own structure and individual colour combination. An image or a sample will therefore never be able to give you a complete picture of the finished floor. Please also note that the colour may change when exposed to light. As a guideline, darker wood species will get a more golden tone, whereas lighter species will become slightly darker. Cracked knots are filled with putty, so small gaps between the putty and wood may appear.