

Wood   Oak   Number of slotted top layers   1   Fire protection classification   Cfl-s1     Grading   Animoso   Surface structure   unbrushed   Content of formaldehyde   E 1		10036347 (EIGV45FD)	Bevel	beveled 2V	Moisture content	5-9%
Grading Animoso Surface structure unbrushed Content of formaldehyde E 1	Wood	Oak	Number of slotted top layers	1	Fire protection classification	Cfl-s1
	Grading	Animoso	Surface structure	unbrushed	Content of formaldehyde	E 1
Product type 3-layer parquet m² per carton 2,76 PCP content NPD	Product type	3-layer parquet	m² per carton	2,76	PCP content	NPD
Format 14mm Plank Castle Boards per carton 6 Brinell Value (N/mm²) 38	Format	14mm Plank Castle	Boards per carton	6	Brinell Value (N/mm²)	38
Dimensions 14 x 209 x 2200 mm Weight per carton (kg) 21,5 Shrinking and swelling	Dimensions	14 x 209 x 2200 mm	Weight per carton (kg)	21,5	Shrinking and swelling	
Top layer thickness 3,5 mm m² per pallet 138 Breaking strength NPD	Top layer thickness	3,5 mm	m² per pallet	138	Breaking strength	NPD
Core material Spruce / Spruce Boxes per pallet 50 Thermal conductivity (W/(m*K) 0,129	Core material	Spruce / Spruce	Boxes per pallet	50	Thermal conductivity (W/(m*K)	0,129
Connection 5G Click Weight per pallet (kg) 1075 Thermal resistance (m <sup>2*</sup> K)/W 0,109	Connection	5G Click	Weight per pallet (kg)	1075	Thermal resistance (m <sup>2*</sup> K)/W	0,109
Floor heating suitable EN Norm EN 13489 Antislip performance (CE) USRV 33	Floor heating	suitable	EN Norm	EN 13489	Antislip performance (CE)	USRV 33
Treatment Live Matt lacquer FSC claim controlled sources Antislip performance (DIN) R9	Treatment	Live Matt lacquer	FSC claim	controlled sources	Antislip performance (DIN)	R9
AppearanceGolden floorsBiological durabilityClass 1Nobb.number43830723	Appearance	Golden floors	Biological durability	Class 1	Nobb.number	43830723
Colour       Transparent       Density       >= 500kg/m³       EAN Code       7035580047919	Colour	Transparent	Density	>= 500kg/m³	EAN Code	7035580047919















Wood is a product of nature – each tree has its own structure and individual colour combination. An image or a sample will therefore never be able to give you a complete picture of the finished floor. Please also note that the colour may change when exposed to light. As a guideline, darker wood species will get a more golden tone, whereas lighter species will become slightly darker. Cracked knots are filled with putty, so small gaps between the putty and wood may appear.

