



Oak Sand Traditional

Product details / Technical properties

Article number	10036586 (XHCX4MFD)	Bevel	beveled 4V	Moisture content	5-9%
Wood	Oak	Number of slotted top layers	0	Fire protection classification	Dfl-s1
Grading	Traditional	Surface structure	unbrushed	Content of formaldehyde	E 1
Product type	3-layer parquet	m² per carton		PCP content	NPD
Format	20mm Plank Chalet	Boards per carton		Brinell Value (N/mm²)	38
Dimensions	20 x 200-395 x 2000-4000 mm	Weight per carton (kg)	11,152	Shrinking and swelling	
Top layer thickness	4,5 mm	m² per pallet	0	Breaking strength	NPD
Core material	Spruce / Spruce	Boxes per pallet		Thermal conductivity (W/(m*K))	0,128
Connection	T/G	Weight per pallet (kg)	0	Thermal resistance (m²*K)/W	0,156
Floor heating	suitable	EN Norm	EN 13489	Antislip performance (CE)	USRV 59
Treatment	Live Natural oil	FSC claim	controlled sources	Antislip performance (DIN)	R10
Appearance	Grey floors	Biological durability	Class 1	Nobb.number	46308621
Colour	Sand	Density	>= 500kg/m ³	EAN Code	7035580137825



Wood is a product of nature – each tree has its own structure and individual colour combination. An image or a sample will therefore never be able to give you a complete picture of the finished floor. Please also note that the colour may change when exposed to light. As a guideline, darker wood species will get a more golden tone, whereas lighter species will become slightly darker. Cracked knots are filled with putty, so small gaps between the putty and wood may appear.