



Ash White Andante

Product details / Technical properties

Article number	10036645 (ASG832PD)	Bevel	without bevel	Moisture content	5-9%
Wood	Ash	Number of slotted top layers	2	Fire protection classification	Dfl-s1
Grading	Andante	Surface structure	sanded	Content of formaldehyde	E 1
Product type	3-layer parquet	m² per carton	3,04	PCP content	NPD
Format	14mm Plank 138	Boards per carton	10	Brinell Value (N/mm²)	36
Dimensions	14 x 138 x 2200 mm	Weight per carton (kg)	25,5	Shrinking and swelling	
Top layer thickness	3,5 mm	m² per pallet	127,68	Breaking strength	NPD
Core material	Spruce / Spruce	Boxes per pallet	42	Thermal conductivity (W/(m²K))	0,125
Connection	5G Click	Weight per pallet (kg)	1071	Thermal resistance (m²K)/W	0,112
Floor heating	suitable	EN Norm	EN 13489	Antislip performance (CE)	USRV 33
Treatment	Live Matt lacquer	FSC claim	controlled sources	Antislip performance (DIN)	R9
Appearance	Light floors	Performance classification	Class 1	Nobb.number	43667237
Colour	White	Density	>= 500kg/m ³	EAN Code	7035580046042



TESTED PRODUCT
ID 0921 - 33879 - 003



06

Boen AS

Topdatumen: 404-404, 4458 T-Web, Norway

Parquet flooring according to:

EN 13489-2017-12 and EN 14342-2013

9,5-23 mm total thickness;

parquet for indoor use

DOP 4658, NB 0766

Dfl-s1; EI density >= 500kg/m³

thermal conductivity >= 0,14 W/mK

Wood is a product of nature – each tree has its own structure and individual colour combination. An image or a sample will therefore never be able to give you a complete picture of the finished floor. Please also note that the colour may change when exposed to light. As a guideline, darker wood species will get a more golden tone, whereas lighter species will become slightly darker. Cracked knots are filled with putty, so small gaps between the putty and wood may appear.