



Oak Pearl Animoso

Product details / Technical properties

Article number	10037193 (ORG84MFD)	Bevel	beveled 2V	Moisture content	5-9%
Wood	Oak	Number of slotted top layers	2	Fire protection classification	Dfl-s1
Grading	Animoso	Surface structure	unbrushed	Content of formaldehyde	E 1
Product type	3-layer parquet	m² per carton	3,04	PCP content	NPD
Format	14mm Plank 138	Boards per carton	10	Brinell Value (N/mm²)	38
Dimensions	14 x 138 x 2200 mm	Weight per carton (kg)	22,7	Shrinking and swelling	
Top layer thickness	3,5 mm	m² per pallet	127,68	Breaking strength	NPD
Core material	Spruce / Spruce	Boxes per pallet	42	Thermal conductivity (W/(m*K))	0,129
Connection	5G Click	Weight per pallet (kg)	953,4	Thermal resistance (m²*K)/W	0,109
Floor heating	suitable	EN Norm	EN 13489	Antislip performance (CE)	USRV 59
Treatment	Live Natural oil	FSC claim	controlled sources	Antislip performance (DIN)	R10
Appearance	Light floors	Biological durability	Class 1	Nobb.number	45965114
Colour	Pearl	Density	>= 500kg/m³	EAN Code	7035580080732



www.blauer-engel.de/uz176



CERTIFIED BY FSC Global Services



Wood is a product of nature – each tree has its own structure and individual colour combination. An image or a sample will therefore never be able to give you a complete picture of the finished floor. Please also note that the colour may change when exposed to light. As a guideline, darker wood species will get a more golden tone, whereas lighter species will become slightly darker. Cracked knots are filled with putty, so small gaps between the putty and wood may appear.