

5-9%	Moisture content	beveled 2V	Bevel	10037212 (PBG843FD)	Article number
Dfl-s1	Fire protection classification	2	Number of slotted top layers	Oak	Wood
E 1	Content of formaldehyde	brushed	Surface structure	Animoso	Grading
NPD	PCP content	3,04	m² per carton	3-layer parquet	Product type
38	Brinell Value (N/mm²)	10	Boards per carton	14mm Plank 138	Format
	Shrinking and swelling	23,5	Weight per carton (kg)	14 x 138 x 2200 mm	Dimensions
NPD	Breaking strength	127,68	m² per pallet	3,5 mm	Top layer thickness
0,129	Thermal conductivity (W/(m*K)	42	Boxes per pallet	Spruce / Spruce	Core material
0,109	Thermal resistance (m ^{2*} K)/W	987	Weight per pallet (kg)	5G Click	Connection
USRV 91	Antislip performance (CE)	EN 13489	EN Norm	suitable	Floor heating
R11	Antislip performance (DIN)	controlled sources	FSC claim	Live Pure lacquer	Treatment
NPD 38 NPD 0,129 0,109 USRV 91	PCP content Brinell Value (N/mm²) Shrinking and swelling Breaking strength Thermal conductivity (W/(m*K) Thermal resistance (m²*K)/W Antislip performance (CE)	3,04 10 23,5 127,68 42 987 EN 13489	m² per carton Boards per carton Weight per carton (kg) m² per pallet Boxes per pallet Weight per pallet (kg) EN Norm	3-layer parquet 14mm Plank 138 14 x 138 x 2200 mm 3,5 mm Spruce / Spruce 5G Click suitable	Product type Format Dimensions Top layer thickness Core material Connection Floor heating

Class 1

>= 500kg/m³



Grey floors

Grey Harmony



Density

Biological durability







Nobb.number

EAN Code





50710433

7035580182474

Wood is a product of nature – each tree has its own structure and individual colour combination. An image or a sample will therefore never be able to give you a complete picture of the finished floor. Please also note that the colour may change when exposed to light. As a guideline, darker wood species will get a more golden tone, whereas lighter species will become slightly darker. Cracked knots are filled with putty, so small gaps between the putty and wood may appear.



Appearance

Colour