

Oak Coral Finale

10041818 (OPGLTMTD) Article number Oak Wood Grading Finale Product type 3-layer parquet Format 14mm Longstrip 3-Strip 14 x 215 x 2200 mm Dimensions Top layer thickness 3,5 mm Core material Spruce / Spruce Connection 5G Click Floor heating suitable Live Natural oil Treatment Appearance Light floors Colour Coral

| Bevel |
|----------------------------|
| Number of slotted top laye |
| Surface structure |
| m² per carton |
| Boards per carton |
| Weight per carton (kg) |
| m² per pallet |
| Boxes per pallet |
| Weight per pallet (kg) |
| EN Norm |
| FSC claim |
| Biological durability |
| Density |

INSTITUT TESTED PRODUCT ID 0921 - 33879 - 003

| | without bevel |
|------|--------------------|
| yers | 0 |
| | sanded |
| | 2,84 |
| | 6 |
| | 21 |
| | 142 |
| | 50 |
| | 1050 |
| | EN 13489 |
| | controlled sources |
| | Class 1 |
| | |

| without bevel | Moisture content |
|--------------------|--|
| 0 | Fire protection classification |
| sanded | Content of formaldehyde |
| 2,84 | PCP content |
| 6 | Brinell Value (N/mm²) |
| 21 | Shrinking and swelling |
| 142 | Breaking strength |
| 50 | Thermal conductivity (W/(m*K) |
| 1050 | Thermal resistance (m ^{2*} K)/W |
| EN 13489 | Antislip performance (CE) |
| controlled sources | Antislip performance (DIN) |
| Class 1 | Nobb.number |
| >= 500kg/m³ | EAN Code |

C CERTIFIED BY SCS Global Service





| | CE |
|----|--|
| | 06 |
| | Boen AS |
| To | pdalsveien 406-408, 4658 Tveit, Norway |
| 8 | Parquet flooring according to IN 13489: 2017-12 and EN 14342:2013 9.5-23 mm total thickness: parquet for indoor use |
| | DOP 4658; NB 0766 |
| | Dfl-sl; EL density >= 500kg/m ^s thermal conductivity >= 0.14 W/mK |

Wood is a product of nature - each tree has its own structure and individual colour combination. An image or a sample will therefore never be able to give you a complete picture of the finished floor. Please also note that the colour may change when exposed to light. As a guideline, darker wood species will get a more golden tone, whereas lighter species will become slightly darker. Cracked knots are filled with putty, so small gaps between the putty and wood may appear.

/uz176



Product details / Technical properties

5-9%

Dfl-s1

E 1

NPD

38

NPD

0,13

0,11 USRV 59

R10

50693663

7035580186427