




Oak Sand Finale

Product details / Technical properties

Article number	10041819 (XHGLTMTD)	Bevel	square edged	Moisture content	5-9%
Wood	Oak	Number of slotted top layers	0	Fire protection classification	Dfl-s1
Grading	Finale	Surface structure	sanded	Content of formaldehyde	E1
Product type	3-Layer	m² per carton	2,84	PCP content	NPD
Format	14mm Longstrip 3-Strip	Boards per carton	6	Brinell Value (N/mm²)	38
Dimensions	9/16 x 8-15/32 x 86-5/8 inch	Weight per carton (kg)	21	Shrinking and swelling	
Top layer thickness	3,5 mm	m² per pallet	142	Breaking strength	NPD
Core material	Spruce / Spruce	Boxes per pallet	50	Thermal conductivity (W/(m*K))	0,13
Connection	5G Click	Weight per pallet (kg)	1050	Thermal resistance (m²*K)/W	0,11
Floor heating	suitable	EN Norm	EN 13489	Antislip performance (CE)	USRV 59
Treatment	Live Natural oil	FSC claim	controlled sources	Antislip performance (DIN)	R10
Appearance	Grey	Performance classification	Class 1	Nobb.number	50693625
Colour	Sand	Density	>= 500kg/m³	EAN Code	7035580186533



Wood is a product of nature – each tree has its own structure and individual colour combination. An image or a sample will therefore never be able to give you a complete picture of the finished floor. Please also note that the colour may change when exposed to light. As a guideline, darker wood species will get a more golden tone, whereas lighter species will become slightly darker. Cracked knots are filled with putty, so small gaps between the putty and wood may appear.