



## Oak Brazilian Brown Animoso

### Product details / Technical properties

<b>Article number</b>	10125138 (PLGV43FD)	<b>Bevel</b>	beveled 2V	<b>Moisture content</b>	5-9%
<b>Wood</b>	Oak	<b>Number of slotted top layers</b>	1	<b>Fire protection classification</b>	Dfl-s1
<b>Grading</b>	Animoso	<b>Surface structure</b>	deep brushed	<b>Content of formaldehyde</b>	E 1
<b>Product type</b>	3-layer parquet	<b>m<sup>2</sup> per carton</b>	2,76	<b>PCP content</b>	NPD
<b>Format</b>	14mm Plank Castle	<b>Boards per carton</b>	6	<b>Brinell Value (N/mm<sup>2</sup>)</b>	38
<b>Dimensions</b>	14 x 209 x 2200 mm	<b>Weight per carton (kg)</b>	24	<b>Shrinking and swelling</b>	
<b>Top layer thickness</b>	3.5 mm	<b>m<sup>2</sup> per pallet</b>	138	<b>Breaking strength</b>	NPD
<b>Core material</b>	Spruce / Spruce	<b>Boxes per pallet</b>	50	<b>Thermal conductivity (W/(m*K))</b>	0,129
<b>Connection</b>	5G Click	<b>Weight per pallet (kg)</b>	1200	<b>Thermal resistance (m<sup>2</sup>K)/W</b>	0,109
<b>Floor heating</b>	suitable	<b>EN Norm</b>	EN 13489	<b>Antislip performance (CE)</b>	USRV 91
<b>Treatment</b>	Live Pure lacquer	<b>FSC claim</b>	controlled sources	<b>Antislip performance (DIN)</b>	R11
<b>Appearance</b>	Brown floors	<b>Performance classification</b>	Class 1	<b>Nobb.number</b>	54522364
<b>Colour</b>	Brazilian Brown	<b>Density</b>	>= 500kg/m <sup>3</sup>	<b>EAN Code</b>	7035580208372



**TESTED PRODUCT**  
ID 0921 - 33879 - 003



CERTIFIED BY  
SCS Global Services



REAL WOOD  
www.realwood.eu



[www.blauer-engel.de/uz176](http://www.blauer-engel.de/uz176)



CE

D6

Boen AS

Topdækket: 40N-40R, 45M8 T-vekt, Norway

Parquet flooring according to  
EN 13489-2017-12 and EN 14926-2013  
9,5-23 mm total thickness  
parquet for indoor use

DOP 4658, NB 0766

Dfl-s1, EI, density >= 500kg/m<sup>3</sup>

thermal conductivity >= 0,14 W/mK

Wood is a product of nature – each tree has its own structure and individual colour combination. An image or a sample will therefore never be able to give you a complete picture of the finished floor. Please also note that the colour may change when exposed to light. As a guideline, darker wood species will get a more golden tone, whereas lighter species will become slightly darker. Cracked knots are filled with putty, so small gaps between the putty and wood may appear.