



Oak White Vivo

Product details / Technical properties

Article number	10125647 (EIG8V2FD)	Bevel	beveled 2V	Moisture content	5-9%
Wood	Oak	Number of slotted top layers	2	Fire protection classification	Cfl-s1
Grading	Vivo	Surface structure	unbrushed	Content of formaldehyde	E 1
Product type	3-layer parquet	m² per carton	3,04	PCP content	NPD
Format	14mm Plank 138	Boards per carton	10	Brinell Value (N/mm²)	38
Dimensions	14 x 138 x 2200 mm	Weight per carton (kg)	23,5	Shrinking and swelling	
Top layer thickness	3,5 mm	m² per pallet	127,68	Breaking strength	NPD
Core material	Spruce / Spruce	Boxes per pallet	42	Thermal conductivity (W/(m*K))	0,129
Connection	5G Click	Weight per pallet (kg)	987	Thermal resistance (m²*K)/W	0,109
Floor heating	suitable	EN Norm	EN 13489	Antislip performance (CE)	USRV 33
Treatment	Live Matt lacquer white	FSC claim	controlled sources	Antislip performance (DIN)	R9
Appearance	Light floors	Biological durability	Class 1	Nobb.number	56807463
Colour	White	Density	>= 500kg/m ³	EAN Code	7035580209058



CE
Boen AS
Topdalsveien 406-408, 4458 Tved, Norway
Parquet flooring according to EN 15489:2017-12 and EN 14342:2015 5,5-23 mm total thickness, parquet for indoor use
DOP 4658, NB 0766
Df=41, E1 density = 500kg/m ³ , thermal conductivity = 0,14 W/mK

Wood is a product of nature – each tree has its own structure and individual colour combination. An image or a sample will therefore never be able to give you a complete picture of the finished floor. Please also note that the colour may change when exposed to light. As a guideline, darker wood species will get a more golden tone, whereas lighter species will become slightly darker. Cracked knots are filled with putty, so small gaps between the putty and wood may appear.