



Oak Adagio

Product details / Technical properties

| | | | | | |
|----------------------------|---|-------------------------------------|--------------------|---------------------------------------|---------------|
| Article number | 10126794 / EBG82KMD | Bevel | beveled 4V | Moisture content | 5-9% |
| Wood | Oak | Number of slotted top layers | 0 | Fire protection classification | Dfl-s1 |
| Grading | Adagio | Surface structure | brushed | Content of formaldehyde | E 1 |
| Product type | 3-layer parquet | m² per carton | 0,95 | PCP content | NPD |
| Format | 14mm Plank Herringbone Click 138, A-Plank | Boards per carton | 10 | Brinell Value | 38 |
| Dimensions | 14 x 138 x 690 mm | Weight per carton (kg) | 10,7 | Shrinking and swelling | |
| Top layer thickness | 3,5 mm | m² per pallet | 46,55 | Breaking strength | NPD |
| Core material | HDF / Spruce | Boxes per pallet | 49 | Thermal conductivity (W/(m*K)) | 0,143 |
| Connection | 5G Click | Weight per pallet (kg) | 524,3 | Thermal resistance (m²*K)/W | 0,098 |
| Floor heating | suitable | EN Norm | EN 13489 | Antislip performance (CE) | USRV 45 |
| Treatment | Live Natural oil | FSC claim | controlled sources | Antislip performance (DIN) | R10 |
| Appearance | Golden floors | Performance classification | Class 1 | Nobb.number | 55493998 |
| Colour | | Density | >= 500kg/m³ | EAN Code | 7035580210573 |



www.blauer-engel.de/uz176

| |
|--|
| CE |
| 06 |
| Boen AS |
| <small>Toppåstøttemen 420-426, 4456 Trondheim, Norway</small> |
| <small>Parquet flooring according to EN 13489:2017-12 and EN 14342:2013 9,5-23 mm total thickness, parquet for indoor use.</small> |
| <small>DOP 4458, H0 0765</small> |
| <small>DIN-6: EI, density ~ 520kg/m³ thermal conductivity ~ 0,14 W/mK</small> |

Wood is a product of nature – each tree has its own structure and individual colour combination. An image or a sample will therefore never be able to give you a complete picture of the finished floor. Please also note that the colour may change when exposed to light. As a guideline, darker wood species will get a more golden tone, whereas lighter species will become slightly darker. Cracked knots are filled with putty, so small gaps between the putty and wood may appear.