



## Ash Baltic

### Product details / Technical properties

|                            |                                         |                                     |              |                                       |               |
|----------------------------|-----------------------------------------|-------------------------------------|--------------|---------------------------------------|---------------|
| <b>Article number</b>      | 10135563 (AS3L85TY)                     | <b>Bevel</b>                        | square edged | <b>Moisture content</b>               | 5-9%          |
| <b>Wood</b>                | Ash                                     | <b>Number of slotted top layers</b> | 1            | <b>Fire protection classification</b> | Dfl-s1        |
| <b>Grading</b>             | Baltic                                  | <b>Surface structure</b>            | unbrushed    | <b>Content of formaldehyde</b>        | E 1           |
| <b>Product type</b>        | 3-layer parquet                         | <b>m² per carton</b>                | 1,89         | <b>PCP content</b>                    | NPD           |
| <b>Format</b>              | Longstrip 21 mm<br>Longstrip Strongline | <b>Boards per carton</b>            | 4            | <b>Brinell Value (N/mm²)</b>          | 36            |
| <b>Dimensions</b>          | 21 x 215 x 2200 mm                      | <b>Weight per carton (kg)</b>       | 21,5         | <b>Shrinking and swelling</b>         |               |
| <b>Top layer thickness</b> | 5,5 mm                                  | <b>m² per pallet</b>                | 94,5         | <b>Breaking strength</b>              | NPD           |
| <b>Core material</b>       | Spruce / Spruce                         | <b>Boxes per pallet</b>             | 50           | <b>Thermal conductivity (W/(m*K))</b> |               |
| <b>Connection</b>          | T/G                                     | <b>Weight per pallet (kg)</b>       | 1075         | <b>Thermal resistance (m²K)/W</b>     |               |
| <b>Floor heating</b>       | conditionally suitable                  | <b>EN Norm</b>                      | EN 13489     | <b>Antislip performance (CE)</b>      | USRV 33       |
| <b>Treatment</b>           | Live Matt lacquer                       | <b>FSC claim</b>                    | FSC™ Mix 70% | <b>Antislip performance (DIN)</b>     | R9            |
| <b>Appearance</b>          | Light floors                            | <b>Biological durability</b>        | Class 1      | <b>Nobb.number</b>                    | 53111058      |
| <b>Colour</b>              |                                         | <b>Density</b>                      | >= 500kg/m³  | <b>EAN Code</b>                       | 7035580211501 |



Wood is a product of nature – each tree has its own structure and individual colour combination. An image or a sample will therefore never be able to give you a complete picture of the finished floor. Please also note that the colour may change when exposed to light. As a guideline, darker wood species will get a more golden tone, whereas lighter species will become slightly darker. Cracked knots are filled with putty, so small gaps between the putty and wood may appear.