



Oak Transparent Semi Smoked Animoso

Product details / Technical properties

| | | | | | |
|----------------------------|---------------------|-------------------------------------|-------------------------|---|---------------|
| Article number | 10144026 (EOGV4KFD) | Bevel | beveled 2V | Moisture content | 5-9% |
| Wood | Oak | Number of slotted top layers | 1 | Fire protection classification | Dfl-s1 |
| Grading | Animoso | Surface structure | brushed | Content of formaldehyde | E 1 |
| Product type | 3-layer parquet | m² per carton | 2,76 | PCP content | NPD |
| Format | 14mm Plank Castle | Boards per carton | 6 | Brinell Value (N/mm²) | 38 |
| Dimensions | 14 x 209 x 2200 mm | Weight per carton (kg) | 20 | Shrinking and swelling | |
| Top layer thickness | 3,5 mm | m² per pallet | 138 | Breaking strength | NPD |
| Core material | Spruce / Spruce | Boxes per pallet | 50 | Thermal conductivity (W/(m*K)) | 0,129 |
| Connection | 5G Click | Weight per pallet (kg) | 1000 | Thermal resistance (m²*K)/W | 0,109 |
| Floor heating | suitable | EN Norm | EN 13489 | Antislip performance (CE) | USRV 45 |
| Treatment | Live Natural oil | FSC claim | controlled sources | Antislip performance (DIN) | R10 |
| Appearance | Brown floors | Biological durability | Class 1 | Nobb.number | 60004833 |
| Colour | Transparent | Density | >= 500kg/m ³ | EAN Code | 7035580216872 |



www.blauer-engel.de/uz176



CERTIFIED BY SCS Global Services



| |
|--|
| CE |
| 06 |
| Boen AS |
| Topdalsveien 406-408, 4408 Tved, Norway |
| Parquet flooring according to EN 13489: 2017-02 and EN 14342:2013, 6,5-23 mm total thickness, parquet for indoor use |
| DOP 4658, NB 0786 |
| Df-s1; E1; density >= 500kg/m ³ ; thermal conductivity <= 0,14 W/mK |

Wood is a product of nature – each tree has its own structure and individual colour combination. An image or a sample will therefore never be able to give you a complete picture of the finished floor. Please also note that the colour may change when exposed to light. As a guideline, darker wood species will get a more golden tone, whereas lighter species will become slightly darker. Cracked knots are filled with putty, so small gaps between the putty and wood may appear.