Oak Indian Summer Vivo

Product details / Technical properties

Article number	10152556 (SVGVVKFD)	**Bevel**	beveled 2V	**Moisture content**	5-9%
Wood	Oak	**Number of slotted top layers**	1	**Fire protection classification**	Dfl-s1
Grading	Vivo	**Surface structure**	double brushed	**Content of formaldehyde**	E 1
Product type	3-layer parquet	**m² per carton**	2,76	**PCP content**	NPD
Format	14mm Plank Castle	**Boards per carton**	6	**Brinell Value (N/mm²)**	38
Dimensions	14 x 209 x 2200 mm	**Weight per carton (kg)**	21,5	**Shrinking and swelling**	
Top layer thickness	3,5 mm	**m² per pallet**	138	**Breaking strength**	NPD
Core material	Spruce / Spruce	**Boxes per pallet**	50	**Thermal conductivity (W/(m*K)**	0,129
Connection	5G Click	**Weight per pallet (kg)**	1075	**Thermal resistance (m²*K)/W**	0,109
Floor heating	suitable	**EN Norm**	EN 13489	**Antislip performance (CE)**	USRV 45
Treatment	Live Natural oil	**FSC claim**	controlled sources	**Antislip performance (DIN)**	R10
Appearance	Golden floors	**Biological durability**	Class 1	**Nobb.number**	60004835
Colour	Indian Summer	**Density**	>= 500kg/m³	**EAN Code**	7035580219446

ECO INSTITUT TESTED PRODUCT ID 0921 - 33879 - 003

BLAUER ENGEL DAS UMWELTZEICHEN www.blauer-engel.de/uz176

floor score CERTIFIED BY SCS Global Services

FDES VÉRIFIÉE inies

REAL WOOD www.realwood.eu

CE

06

Boen AS

Toppdalsveien 406-408, 6658 Tvelt, Norway

Parquet flooring according to EN 13489: 2017-12 and EN 14342:2013 9,5-23 mm total thickness, parquet for indoor use

DOP 4658, NB 0766

Dfl-s1, El, density >= 500kg/m³ thermal conductivity >= 0,14 W/mK

Wood is a product of nature – each tree has its own structure and individual colour combination. An image or a sample will therefore never be able to give you a complete picture of the finished floor. Please also note that the colour may change when exposed to light. As a guideline, darker wood species will get a more golden tone, whereas lighter species will become slightly darker. Cracked knots are filled with putty, so small gaps between the putty and wood may appear.