

WoodOakNumber of slotted top layers2Fire protection classificationDfl-s1GradingAnimoso MixSurface structurebrushedContent of formaldehydeE 1Product type3-layer parquetm² per carton3,04PCP contentNPDFormat14mm Plank 138Boards per carton10Brinell Value (N/mm²)38Dimensions14 x 138 x 2200 mmWeight per carton (kg)23,5Shrinking and swellingTop layer thickness3,5 mmm² per pallet127,68Breaking strengthNPDCore materialSpruce / SpruceBoxes per pallet42Thermal conductivity (W/(m*K))0,129
Product type 3-layer parquet m² per carton 3,04 PCP content NPD Format 14mm Plank 138 Boards per carton 10 Brinell Value (N/mm²) 38 Dimensions 14 x 138 x 2200 mm Weight per carton (kg) 23,5 Shrinking and swelling Top layer thickness 3,5 mm m² per pallet 127,68 Breaking strength NPD
Format 14mm Plank 138 Boards per carton 10 Brinell Value (N/mm²) 38 Dimensions 14 x 138 x 2200 mm Weight per carton (kg) 23,5 Shrinking and swelling Top layer thickness 3,5 mm m² per pallet 127,68 Breaking strength NPD
Dimensions 14 x 138 x 2200 mm Weight per carton (kg) 23,5 Shrinking and swelling Top layer thickness 3,5 mm m² per pallet 127,68 Breaking strength NPD
Top layer thickness 3,5 mm m² per pallet 127,68 Breaking strength NPD
Core meterial Society (NV/m*V) 0.100
Sproce / Sproce Boxes per paner 42 mermal conductivity (W/(iii k) 0,127
Connection 5G Click Weight per pallet (kg) 987 Thermal resistance (m ^{2*} K)/W 0,109
Floor heating suitable EN Norm EN 13489 Antislip performance (CE) USRV 57
Treatment Live Matt Plus lacquer FSC claim controlled sources Antislip performance (DIN)
AppearanceBrown floorsBiological durabilityClass 1Nobb.number60004821
Colour Soft Brown Density >= 500kg/m³ EAN Code 7035580219491















Wood is a product of nature – each tree has its own structure and individual colour combination. An image or a sample will therefore never be able to give you a complete picture of the finished floor. Please also note that the colour may change when exposed to light. As a guideline, darker wood species will get a more golden tone, whereas lighter species will become slightly darker. Cracked knots are filled with putty, so small gaps between the putty and wood may appear.

