

Oak Espresso Live Pure

Product details / Technical properties

Article number	10155752 (EBH8Z3FE)	Bevel	beveled 2V	Moisture content	5-9%
Wood	Oak	Number of slotted top layers	3	Fire protection classification	Dfl-s1
Grading	Espresso	Surface structure	brushed	Content of formaldehyde	E 1
Product type	3-layer parquet	m² per carton	3,04	PCP content	NPD
Format	Plank 13mm Plank 138	Boards per carton	10	Brinell Value (N/mm²)	38
Dimensions	13 x 138 x 2200 mm	Weight per carton (kg)	21,9	Shrinking and swelling	
Top layer thickness	2,5 mm	m² per pallet	127,68	Breaking strength	NPD
Core material	Spruce / Spruce	Boxes per pallet	42	Thermal conductivity (W/(m*K))	0,127
Connection	5G Click	Weight per pallet (kg)	919,8	Thermal resistance (m²*K)/W	0,103
Floor heating	suitable	EN Norm	EN 13489	Antislip performance (CE)	USRV 91
Treatment	Live Pure lacquer	FSC claim	controlled sources	Antislip performance (DIN)	R11
Appearance	Golden floors	Performance classification	Class 1	Nobb.number	60084639
Colour		Density	>= 500kg/m³	EAN Code	7035580222675



www.blauer-engel.de/liz176

CE
GS
Boen AS
Topplatteneier 406-408, 4458 Tveit, Norway
Parquet flooring according to EN 13489-2:2017-10 and EN 14342:2013, 9,5-23 mm total thickness, parquet for indoor use
DOP 4658, NB 0756
Dfl-s1, EI, density >= 500kg/m³, thermal conductivity <= 0,14 W/mK

Wood is a product of nature – each tree has its own structure and individual colour combination. An image or a sample will therefore never be able to give you a complete picture of the finished floor. Please also note that the colour may change when exposed to light. As a guideline, darker wood species will get a more golden tone, whereas lighter species will become slightly darker. Cracked knots are filled with putty, so small gaps between the putty and wood may appear.