



Oak Authentic Espresso

Product details / Technical properties

| | | | | | |
|----------------------------|----------------------|-------------------------------------|-------------------------|---|---------------|
| Article number | 10157183 | Bevel | beveled 2V | Moisture content | 5-9% |
| Wood | Oak | Number of slotted top layers | 1 | Fire protection classification | Dfl-s1 |
| Grading | Espresso | Surface structure | deep brushed | Content of formaldehyde | E 1 |
| Product type | 3-layer parquet | m² per carton | 3.19 | PCP content | NPD |
| Format | 13.2mm Plank 181 | Boards per carton | 8 | Brinell Value (N/mm²) | 38 |
| Dimensions | 13.2 x 181 x 2200 mm | Weight per carton (kg) | 23 | Shrinking and swelling | |
| Top layer thickness | 2.7 mm | m² per pallet | 127.6 | Breaking strength | NPD |
| Core material | Spruce / Spruce | Boxes per pallet | 40 | Thermal conductivity (W/(m*K)) | 0.127 |
| Connection | 5G@ Click | Weight per pallet (kg) | 920 | Thermal resistance (m²*K)/W | 0.104 |
| Floor heating | suitable | EN Norm | EN 13489 | Antislip performance (CE) | USRV 45 |
| Treatment | Live Natural oil | FSC claim | controlled sources | Antislip performance (DIN) | R10 |
| Appearance | Golden floors | Performance classification | Class 1 | Nobb.number | 60090630 |
| Colour | Authentic | Density | >= 500kg/m ³ | EAN Code | 7035580225492 |



Wood is a product of nature – each tree has its own structure and individual colour combination. An image or a sample will therefore never be able to give you a complete picture of the finished floor. Please also note that the colour may change when exposed to light. As a guideline, darker wood species will get a more golden tone, whereas lighter species will become slightly darker. Cracked knots are filled with putty, so small gaps between the putty and wood may appear.