

Wood Oak Number of slotted top layers 1 Fire protection classification Dfl-s1   Grading Espressivo Surface structure brushed Content of formaldehyde E 1   Product type 3-layer parquet m² per carton 3,19 PCP content NPD
Product type 3-layer parquet m² per carton 3,19 PCP content NPD
Farment 12 Owen Direct 101 Be made now a release 0 Defined Medica (N/come)
Format 13,2mm Plank 181 Boards per carton 8 Brinell Value (N/mm²) 38
Dimensions 13,2 x 181 x 2200 mm Weight per carton (kg) 23,5 Shrinking and swelling
Top layer thickness     2,7 mm     m² per pallet     127,6     Breaking strength     NPD
Core material Spruce / Spruce Boxes per pallet 40 Thermal conductivity (W/(m*K) 0,127
Connection 5G Click Weight per pallet (kg) 940 Thermal resistance (m <sup>2*</sup> K)/W 0,104
Floor heating suitable EN Norm EN 13489 Antislip performance (CE) USRV 45
Treatment Live Natural oil FSC claim controlled sources Antislip performance (DIN) R10
AppearanceGolden floorsPerformance classificationClass 1Nobb.number60090630
Colour     Authentic     Density     >= 500kg/m³     EAN Code     7035580225492














Wood is a product of nature – each tree has its own structure and individual colour combination. An image or a sample will therefore never be able to give you a complete picture of the finished floor. Please also note that the colour may change when exposed to light. As a guideline, darker wood species will get a more golden tone, whereas lighter species will become slightly darker. Cracked knots are filled with putty, so small gaps between the putty and wood may appear.

