



Oak Authentic Espresso

Product details / Technical properties

Article number	10157183	Bevel	beveled 2V	Moisture content	5-9%
Wood	Oak	Number of slotted top layers	1	Fire protection classification	Dfl-s1
Grading	Espresso	Surface structure	Brushed	Content of formaldehyde	E1
Product type	3-Layer	m² per carton	3,19	PCP content	NPD
Format	13.2mm Plank 181	Boards per carton	8	Brinell Value (N/mm²)	38
Dimensions	1/2 x 7-1/8 x 86-5/8 inch	Weight per carton (kg)	23,5	Shrinking and swelling	
Top layer thickness	2,7 mm	m² per pallet	127,6	Breaking strength	NPD
Core material	Spruce / Spruce	Boxes per pallet	40	Thermal conductivity (W/(m*K))	0,127
Connection	5G Click	Weight per pallet (kg)	940	Thermal resistance (m²*K)/W	0,104
Floor heating	suitable	EN Norm	EN 13489	Antislip performance (CE)	USRV 45
Treatment	Live Natural oil	FSC claim	controlled sources	Antislip performance (DIN)	R10
Appearance	Golden	Performance classification	Class 1	Nobb.number	60090630
Colour	Authentic	Density	>= 500kg/m³	EAN Code	7035580225492



Wood is a product of nature – each tree has its own structure and individual colour combination. An image or a sample will therefore never be able to give you a complete picture of the finished floor. Please also note that the colour may change when exposed to light. As a guideline, darker wood species will get a more golden tone, whereas lighter species will become slightly darker. Cracked knots are filled with putty, so small gaps between the putty and wood may appear.