

## Oak Transparent Andante

## Product details / Technical properties

REAL

Article number	10157407	Bevel	without bevel	Moisture content	5-9%
Wood	Oak	Number of slotted top layers	0	Fire protection classification	Dfl-s1
Grading	Andante	Surface structure	unbrushed	Content of formaldehyde	E 1
Product type	3-layer parquet	m² per carton	2,84	PCP content	NPD
Format	13.2mm 3-Strip	Boards per carton	6	Brinell Value (N/mm²)	38
Dimensions	13.2 x 215 x 2200 mm	Weight per carton (kg)	21	Shrinking and swelling	
Top layer thickness	2,7 mm	m² per pallet	142	Breaking strength	NPD
Core material	Spruce / Spruce	Boxes per pallet	50	Thermal conductivity (W/(m*K)	0,127
Connection	5G Click	Weight per pallet (kg)	1050	Thermal resistance (m <sup>2</sup> *K)/W	0,104
Floor heating	suitable	EN Norm	EN 13489	Antislip performance (CE)	USRV 59
Treatment	Live Natural oil	FSC claim	controlled sources	Antislip performance (DIN)	R10
Appearance	Golden floors	Biological durability	Class 1	Nobb.number	
Colour	Transparent	Density	>= 500kg/m³	EAN Code	7035580225935





	CE		
	06		
	Boen AS		
Topdalsveien 406-408, 4658 Tveit, Norway			
8	Parquet Rooring according to N 13489: 2017-12 and EN 14342:2013 9.5-23 mm total thickness: parquet for indoor use		
	DOP 4658; NB 0766		
	Dfl-sl; El, density >= 500kg/m <sup>1</sup> thermal conductivity >= 0.14 W/mK		

Wood is a product of nature - each tree has its own structure and individual colour combination. An image or a sample will therefore never be able to give you a complete picture of the finished floor. Please also note that the colour may change when exposed to light. As a guideline, darker wood species will get a more golden tone, whereas lighter species will become slightly darker. Cracked knots are filled with putty, so small gaps between the putty and wood may appear.

