


Oak White Animoso

| Article number | 10157415 |
|---------------------|----------------------|
| Wood | Oak |
| Grading | Animoso |
| Product type | 3-layer parquet |
| Format | 13.2mm Plank 181 |
| Dimensions | 13.2 x 181 x 2200 mr |
| Top layer thickness | 2,7 mm |
| Core material | Spruce / Spruce |
| Connection | 5G Click |
| Floor heating | suitable |
| Treatment | Live Natural oil |
| Appearance | Light floors |
| Colour | White |

Bevel Number of slotted top layers Surface structure m² per carton Boards per carton (kg) Weight per carton (kg) m² per pallet Boxes per pallet Weight per pallet (kg) EN Norm FSC claim Biological durability Density



Class 1

>= 500kg/m³



| Moisture content | 5-9% |
|--------------------------------|---------------|
| Fire protection classification | Dfl-s1 |
| Content of formaldehyde | E 1 |
| PCP content | NPD |
| Brinell Value (N/mm²) | 38 |
| Shrinking and swelling | |
| Breaking strength | NPD |
| Thermal conductivity (W/(m*K) | 0,127 |
| Thermal resistance (m²*K)/W | 0,104 |
| Antislip performance (CE) | USRV 59 |
| Antislip performance (DIN) | R10 |
| Nobb.number | 60090498 |
| EAN Code | 7035580225980 |







| | CE |
|---|--|
| ľ | 06 |
| ſ | Boen AS |
| ſ | Topdalsveien 406-408, 4658 Tveit, Norwa |
| ľ | Parquet flooring according to EN 13489: 2017-12 and EN 14342 2013 9.5-23 mm total thickness; parquet for indoor use |
| ſ | DOP 4658; NB 0766 |
| ľ | Dfl-sl; EL density >= 500kg/m ¹ thermal conductivity >= 0.14 W/mK |

Wood is a product of nature – each tree has its own structure and individual colour combination. An image or a sample will therefore never be able to give you a complete picture of the finished floor. Please also note that the colour may change when exposed to light. As a guideline, darker wood species will get a more golden tone, whereas lighter species will become slightly darker. Cracked knots are filled with putty, so small gaps between the putty and wood may appear.

