

Oak Transparent Semi Smoked Animoso Mix

Product details / Technical properties

Article number	10158873	Bevel	beveled 2V	Moisture content	5-9%
Wood	Oak	Number of slotted top layers	1	Fire protection classification	Dfl-s1
Grading	Animoso Mix	Surface structure	Brushed	Content of formaldehyde	El
Product type	3-Layer	m² per carton	3,19	PCP content	NPD
Format	13.2mm Plank 181	Boards per carton	8	Brinell Value (N/mm²)	38
Dimensions	1/2 x 7-1/8 x 86-5/8 inch	Weight per carton (kg)	23,5	Shrinking and swelling	
Top layer thickness	2,7 mm	m² per pallet	127,6	Breaking strength	NPD
Core material	Spruce / Spruce	Boxes per pallet	40	Thermal conductivity (W/(m*K)	0,13
Connection	5G Click	Weight per pallet (kg)	940	Thermal resistance (m ² *K)/W	0,1
Floor heating	suitable	EN Norm	EN 13489	Antislip performance (CE)	USRV 91
Treatment	Live Pure laquer	FSC claim	controlled sources	Antislip performance (DIN)	R11
Appearance	Brown	Performance classification	Class 1	Nobb.number	53111058
Colour	Transparent	Density	>= 500kg/m³	EAN Code	7035580227717
Product type Format Dimensions Top layer thickness Core material Connection Floor heating Treatment Appearance	3-Layer 13.2mm Plank 181 1/2 x 7-1/8 x 86-5/8 inch 2,7 mm Spruce / Spruce 5G Click suitable Live Pure laquer Brown	m² per carton Boards per carton Weight per carton (kg) m² per pallet Boxes per pallet Weight per pallet (kg) EN Norm FSC claim Performance classification	3,19 8 23,5 127,6 40 940 EN 13489 controlled sources Class 1	PCP content Brinell Value (N/mm²) Shrinking and swelling Breaking strength Thermal conductivity (W/(m*K) Thermal resistance (m²*K)/W Antislip performance (CE) Antislip performance (DIN) Nobb.number	NPD 38 NPD 0,13 0,1 USRV 91 R11 53111058



Wood is a product of nature – each tree has its own structure and individual colour combination. An image or a sample will therefore never be able to give you a complete picture of the finished floor. Please also note that the colour may change when exposed to light. As a guideline, darker wood species will get a more golden tone, whereas lighter species will become slightly darker. Cracked knots are filled with putty, so small gaps between the putty and wood may appear.

