

Oak Pale White Vivo

Product details / Technical properties

| Article number | 10163210 | Bevel | beveled 4V | Moisture content | 5-9% |
|---------------------|------------------------|------------------------------|--------------------|--|---------------|
| Wood | Oak | Number of slotted top layers | 0 | Fire protection classification | Dfl-s1 |
| Grading | Vivo | Surface structure | brushed | Content of formaldehyde | E 1 |
| Product type | 2-layer parquet | m² per carton | 3,25 | PCP content | <=5 ppm |
| Format | Herringbone T/G | Boards per carton | 30 | Brinell Value (N/mm²) | 38 |
| Dimensions | 10.5 x 137 x 790 mm | Weight per carton (kg) | 19 | Shrinking and swelling | |
| Top layer thickness | 3,5 mm | m² per pallet | 104 | Breaking strength | NPD |
| Core material | / Spruce | Boxes per pallet | 32 | Thermal conductivity (W/(m*K) | 0,132 |
| Connection | T/G | Weight per pallet (kg) | 608 | Thermal resistance (m ^{2*} K)/W | 0,079 |
| Floor heating | very suitable | EN Norm | EN 13489 | Antislip performance (CE) | USRV 57 |
| Treatment | Live Matt Plus lacquer | FSC claim | controlled sources | Antislip performance (DIN) | R10 |
| Appearance | Light floors | Biological durability | Class 1 | Nobb.number | |
| Colour | Pale White | Density | >= 500kg/m³ | EAN Code | 7611661203230 |











Wood is a product of nature – each tree has its own structure and individual colour combination. An image or a sample will therefore never be able to give you a complete picture of the finished floor. Please also note that the colour may change when exposed to light. As a guideline, darker wood species will get a more golden tone, whereas lighter species will become slightly darker. Cracked knots are filled with putty, so small gaps between the putty and wood may appear.

