

## Oak Toscana Structure

## Product details / Technical properties

Article number	10163864	Bevel	without bevel	Moisture content	5-9%
Wood	Oak	Number of slotted top layers	2	Fire protection classification	Cfl-s1
Grading	Structure	Surface structure	sanded	Content of formaldehyde	E 1
Product type	2-layer parquet	m² per carton	2,63	PCP content	NPD
Format	10mm Strip Prestige	Boards per carton	80	Brinell Value (N/mm²)	38
Dimensions	10 x 70 x 470 mm	Weight per carton (kg)	15	Shrinking and swelling	
Top layer thickness	3,5 mm	m² per pallet	94,68	Breaking strength	NPD
Core material	/ Spruce	Boxes per pallet	36	Thermal conductivity (W/(m*K)	0,133
Connection	T/G	Weight per pallet (kg)	540	Thermal resistance (m <sup>2</sup> *K)/W	0,075
Floor heating	very suitable	EN Norm	EN 13489	Antislip performance (CE)	USRV 33
Treatment	Live Matt lacquer	FSC claim	controlled sources	Antislip performance (DIN)	R9
Appearance	Golden floors	Biological durability	Class 1	Nobb.number	
Colour	Toscana	Density	>= 500kg/m³	EAN Code	7035580230793







<u> </u>					
					Boen AS
Topdalsveien 406-408, 4658 Tve	t, Norway				
Parquet flooring accordi EN 13489: 2017-12 and EN 14 9,5-23 mm total thickne parquet for indoor us	142:2013 \$3;				
DOP 4658; NB 0766					
Dfl-sl; EL density >= 500kg thermal conductivity >= 0.14					

.

Wood is a product of nature – each tree has its own structure and individual colour combination. An image or a sample will therefore never be able to give you a complete picture of the finished floor. Please also note that the colour may change when exposed to light. As a guideline, darker wood species will get a more golden tone, whereas lighter species will become slightly darker. Cracked knots are filled with putty, so small gaps between the putty and wood may appear.

