

| Article number | 10041631 (ASGL3KTD) | Bevel | square edged | Moisture content | 5-9% |
|---------------------|------------------------|------------------------------|--------------------|--|---------------|
| Wood | Ash | Number of slotted top layers | 0 | Fire protection classification | Dfl-s1 |
| Grading | Andante | Surface structure | unbrushed | Content of formaldehyde | E 1 |
| Product type | 3-layer parquet | m² per carton | 2,84 | PCP content | NPD |
| Format | 14mm Longstrip 3-Strip | Boards per carton | 6 | Brinell Value (N/mm²) | 36 |
| Dimensions | 14 x 215 x 2200 mm | Weight per carton (kg) | 21 | Shrinking and swelling | |
| Top layer thickness | 3,5 mm | m² per pallet | 142 | Breaking strength | NPD |
| Core material | Spruce / Spruce | Boxes per pallet | 50 | Thermal conductivity (W/(m*K) | 0,13 |
| Connection | 5G Click | Weight per pallet (kg) | 1050 | Thermal resistance (m ^{2*} K)/W | 0,11 |
| Floor heating | suitable | EN Norm | EN 13489 | Antislip performance (CE) | USRV 59 |
| Treatment | Live Natural oil | FSC claim | controlled sources | Antislip performance (DIN) | R10 |
| Appearance | Light floors | Biological durability | Class 1 | Nobb.number | 53111058 |
| Colour | Transparent | Density | >= 500kg/m³ | EAN Code | 7035580186618 |














Wood is a product of nature – each tree has its own structure and individual colour combination. An image or a sample will therefore never be able to give you a complete picture of the finished floor. Please also note that the colour may change when exposed to light. As a guideline, darker wood species will get a more golden tone, whereas lighter species will become slightly darker. Cracked knots are filled with putty, so small gaps between the putty and wood may appear.

