

Oak Arizona Concerto

Product details / Technical properties

| WoodOakNumber of slotted top layers2Fire protection classificationCfl-s | fl-s 1 |
|--|--------------|
| | |
| Grading Concerto Surface structure Unbrushed Content of formaldehyde E1 | 1 |
| Product type 3-Layer m ² per carton 3,04 PCP content NPC | PD |
| Format5-1/2" plankBoards per carton10Brinell Value (N/mm²)38 | 3 |
| Dimensions9/16 x 5-7/16 x 86-5/8 inchWeight per carton (kg)23,3Shrinking and swelling | |
| Top layer thickness 3,5 mm m ² per pallet 127,68 Breaking strength NPD | PD |
| Core material Spruce / Spruce Boxes per pallet 42 Thermal conductivity (W/(m*K) 0,12 | 129 |
| Connection5G ClickWeight per pallet (kg)978,6Thermal resistance (m2*K)/W0,10 | 109 |
| Floor heating suitable EN Norm EN 13489 Antislip performance (CE) USR | SRV 33 |
| Treatment Live Matt lacquer FSC claim controlled sources Antislip performance (DIN) R9 | 9 |
| Appearance Grey Performance classification Class 1 Nobb.number 5308 | 3089555 |
| ColourArizonaDensity>= 500kg/m³EAN Code703 | 035580187578 |



Wood is a product of nature – each tree has its own structure and individual colour combination. An image or a sample will therefore never be able to give you a complete picture of the finished floor. Please also note that the colour may change when exposed to light. As a guideline, darker wood species will get a more golden tone, whereas lighter species will become slightly darker. Cracked knots are filled with putty, so small gaps between the putty and wood may appear.

