

| Article number | 10125647 (EIG8V2FD) | Bevel | beveled 2V | Moisture content | 5-9% |
|---------------------|-------------------------|------------------------------|-------------------------|--|---------------|
| Wood | Oak | Number of slotted top layers | 2 | Fire protection classification | Cfl-s1 |
| Grading | Vivo | Surface structure | unbrushed | Content of formaldehyde | E 1 |
| Product type | 3-layer parquet | m² per carton | 3,04 | PCP content | NPD |
| Format | 14mm Plank 138 | Boards per carton | 10 | Brinell Value (N/mm²) | 38 |
| Dimensions | 14 x 138 x 2200 mm | Weight per carton (kg) | 23,5 | Shrinking and swelling | |
| Top layer thickness | 3,5 mm | m² per pallet | 127,68 | Breaking strength | NPD |
| Core material | Spruce / Spruce | Boxes per pallet | 42 | Thermal conductivity (W/(m*K) | 0,129 |
| Connection | 5G Click | Weight per pallet (kg) | 987 | Thermal resistance (m ² *K)/W | 0,109 |
| Floor heating | suitable | EN Norm | EN 13489 | Antislip performance (CE) | USRV 33 |
| Treatment | Live Matt lacquer white | FSC claim | controlled sources | Antislip performance (DIN) | R9 |
| Appearance | Light floors | Biological durability | Class 1 | Nobb.number | 56807463 |
| Colour | White | Density | >= 500kg/m ³ | EAN Code | 7035580209058 |















Wood is a product of nature – each tree has its own structure and individual colour combination. An image or a sample will therefore never be able to give you a complete picture of the finished floor. Please also note that the colour may change when exposed to light. As a guideline, darker wood species will get a more golden tone, whereas lighter species will become slightly darker. Cracked knots are filled with putty, so small gaps between the putty and wood may appear.

